



Polymethyl Methacrylate (PMMA)

SX-302

Items	Test standards	Unit	Data
Optical Properties			
Refractive index	ISO 489	-	1.49
Transmittance	ISO 13468-1	%	93
Fuzzy Coefficient(Haze)	ISO-14782	%	0.3
Thermal properties			
Coefficient of linear thermal expansion	ISO 11359-2	1/°C	7×10 ⁻⁵
Vicat Softening temperature (VST)	ISO 306	°C	89
Load heat distortion temperature 1.82Mpa	ISO 75-2	°C	84
230 °C 3.8 kg melt flow index (MFI)	ISO 1133	g/10min	9.5
Mechanical properties			
Tensile strength	ISO 527-2	Mpa	70
Tensile rate	ISO 527-2	%	4
Bending strength	ISO 178	MPa	120
Flexural modulus	ISO 178	MPa	3200
Charpy impact strength (with notch)	ISO 179-1	KJ/m2	1.4
Rockwell hardness	ISO 2039-2	-	93
Electrical properties			
Surface resistivity	IEC 60093	Ω	> 10 ¹⁶
Volume resistivity	IEC 60093	Ωcm	> 10 ¹⁴
Dielectric coefficient of resistance	IEC 60167	Ω	> 10 ¹⁵

Van Bros Trading Co. Ltd.

Website: <https://vanbroscchemicals.com> E-mail: Info@vanbroscchemicals.com Mobile: +1 (778) 237-8769

Address: 8477 Bridgeport Rd #1005, Richmond BC V6X 0S7 Canada

Dielectric strength	IEC 60243-1	Kv/mm	20
Dielectric constant	IEC 60250	-	3.5

Other properties

Density	ISO 118	-	1.19
Molding shrinkage	ISO 294-4	%	0.2-0.6
Water absorption	ISO 62	%	0.3
Flame retardant	UL 94	-	HB

***The above data is accurate and reliable, but it's only a representative sample of data**

Van Bros Trading Co. Ltd.

Website: <https://vanbroschemicals.com> E-mail: Info@vanbroschemicals.com Mobile: +1 (778) 237-8769

Address: 8477 Bridgeport Rd #1005, Richmond BC V6X 0S7 Canada