



Polymethyl Methacrylate (PMMA)

SX-8S

Items	Test standards	Unit	Data
Optical Properties			
Refractive index	ISO489	-	1.49
Transmittance	ISO13468-1	%	93
Fuzzy Coefficient(Haze)	ISO-14782	%	0.3
Thermal properties			
Coefficient of linear thermal expansion	ISO11359-2	1/°C	8×10 ⁻⁵
Vicat Softening temperature (VST)	ISO306	°C	108
Load heat distortion temperature 1.82Mpa	ISO75-2	°C	98
230 °C 3.8 kg melt flow index (MFI)	ISO 1133	g/10min	3.1
Mechanical properties			
Tensile Modulus	ISO 527-2	Mpa	3300
Tensile strength	ISO 527-2	Mpa	77
Elongation @ Break	ISO 527-2	%	5.5
Charpy impact strength	ISO 179-1	KJ/m2	20
Other properties			
Density	ISO 1183	-	1.19
Water absorption	ISO 62	%	0.3
Flame retardant	UL 94	-	HB

*The above data is accurate and reliable, but it's only a representative sample of data

Van Bros Trading Co. Ltd.

Website: <https://vanbroschemicals.com> E-mail: Info@vanbroschemicals.com Mobile: +1 (778) 237-8769

Address: 8477 Bridgeport Rd #1005, Richmond BC V6X 0S7 Canada